

951 Douglas Road
 Batavia, IL 60510
 (847) 534-6600



Product Data Sheet—ISO

INJECTOBLEND™ FPC120

Impact Modified Polycarbonate

Properties / Reported DAM	Test Method	Metric (S.I.)	Units System
PHYSICAL			
Density	ISO 1183-1	g/cm ³	1.19
Melt Flow Rate @ 220°C / 10kg, nominal	ISO 1133-1	g/10min	20
MECHANICAL			
Tensile Strength @ Yield. (50mm/min, 23°C)	ISO 527-2	MPa	59
Tensile Elongation @ Yield. (50mm/min, 23°C)	ISO 527-2	%	6
Tensile Modulus. (1mm/min, 23°C)	ISO 527-2	GPa	2.46
Flexural Strength. (2mm/min, 23°C)	ISO 178	MPa	80
Flexural Modulus. (2mm/min, 23°C)	ISO 178	MPa	2080
Charpy Impact, notched. (23°C)	ISO 179/1eA	kJ/m ²	65.0
THERMAL			
Deflection Temperature, unannealed (1.8 MPa Load)	ISO 75	°C	126
(0.45 MPa Load)	ISO 75	°C	139
Glass Transition Temperature	ISO 11357-2	°C	143
FLAMMABILITY			
UL 94 Flame Class. 0.058" (1.47mm)	UL 94	-	HB

The values shown on the data sheet are typical values that have been obtained on typical AGS materials, are not intended for specification purposes and are provided without any warranty or guarantee. Each user of the material should make his own test to determine the suitability of the material for his use. Therefore, it is understood and agreed that the customer assumes and hereby releases AGS Technology, Inc. from all liabilities, incurred in connection with the use of AGS products, technical assistance and information. (APR 2023)